

Requested Patent:

WO9421309A1

Title:

POLYURETHANE-COATED INTRAVASCULAR PROSTHESES (STENTS) FOR THE TREATMENT OF BLOOD VESSEL STENOSIS;

Abstracted Patent:

WO9421309;

Publication Date:

1994-09-29;

Inventor(s):

Applicant(s):

DSB NV (BE);

Application Number:

WO1994BE00024 19940324;

Priority Number(s):

BE19930000285 19930324;

IPC Classification:

A61L31/00 ;

Equivalents:

AU6178094, BE1006819

ABSTRACT:

A new method to treat blood vessel stenosis using endovascular prostheses which are coated with amphiphilic polyurethanes to which medicines can be coupled. By coating endovascular prosthesis with amphiphilic polyurethanes, we have succeeded in significantly improving the bio- and bloodcompatibility of endovascular prostheses. These amphiphilic polyurethanes have the property, when implanted in human or animal tissue and blood vessels, of remaining stable and seeming not to provoke an inflammatory reaction. Furthermore it is possible to incorporate medicines in these polymers which, after implantation of the polymers, are slowly released at the location of the place of implantation. This system can further reduce the thrombogenicity of the prostheses coated with the polyurethanes and inhibit the rejection against these prostheses.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



A & 1 I 21/M		(11) International Publication Number: WO 94/21309
A61L 31/00	A1	(43) International Publication Date: 29 September 1994 (29.09.94)
(21) International Application Number: PCT/BI (22) International Filing Date: 24 March 1994		PL, RO, RU, US, European patent (AT, BE, CH, DE, DK
(30) Priority Data: 9300285 24 March 1993 (24.03.93)	F	Published With international search report.
(71) Applicant (for all designated States except US): N. [BE/BE]; Meirbrug 1, Bus 2, B-2000 Antwerp (B		3.
	LAR P	OSTHESES (STENTS) FOR THE TREATMENT OF BLOOD VESSEL
STENOSIS		·
STENOSIS (57) Abstract		
A new method to treat blood vessel stenosis using which medicines can be coupled. By coating endovascular improving the bio- and bloodcompatibility of endovascular in human or animal tissue and blood vessels, of remaining possible to incorporate medicines in these polymers which	r prosthe prosthe stable h, after	esis with amphiphilic polyurethanes, we have succeeded in significantly ses. These amphiphilic polyurethanes have the property, when implanted and seeming not to provoke an inflammatory reaction. Furthermore it is implantation of the polymers, are slowly released at the location of the
A new method to treat blood vessel stenosis using which medicines can be coupled. By coating endovascular mproving the bio- and bloodcompatibility of endovascular n human or animal tissue and blood vessels, of remaining possible to incorporate medicines in these polymers which clace of implantation. This system can further reduce the	r prosthe prosthe stable h, after	esis with amphiphilic polyurethanes, we have succeeded in significantly ses. These amphiphilic polyurethanes have the property, when implanted and seeming not to provoke an inflammatory reaction. Furthermore it is implantation of the polymers, are slowly released at the location of the
A new method to treat blood vessel stenosis using which medicines can be coupled. By coating endovascular mproving the bio- and bloodcompatibility of endovascular n human or animal tissue and blood vessels, of remaining possible to incorporate medicines in these polymers which clace of implantation. This system can further reduce the	r prosthe prosthe stable h, after	esis with amphiphilic polyurethanes, we have succeeded in significantly ses. These amphiphilic polyurethanes have the property, when implanted and seeming not to provoke an inflammatory reaction. Furthermore it is implantation of the polymers, are slowly released at the location of the
A new method to treat blood vessel stenosis using which medicines can be coupled. By coating endovascular mproving the bio- and bloodcompatibility of endovascular n human or animal tissue and blood vessels, of remaining possible to incorporate medicines in these polymers which place of implantation. This system can further reduce the	r prosthe prosthe stable h, after	esis with amphiphilic polyurethanes, we have succeeded in significantly ses. These amphiphilic polyurethanes have the property, when implanted and seeming not to provoke an inflammatory reaction. Furthermore it is implantation of the polymers, are slowly released at the location of the
A new method to treat blood vessel stenosis using which medicines can be coupled. By coating endovascular improving the bio- and bloodcompatibility of endovascular in human or animal tissue and blood vessels, of remaining possible to incorporate medicines in these polymers which place of implantation. This system can further reduce the	r prosthe prosthe stable h, after	esis with amphiphilic polyurethanes, we have succeeded in significantly ses. These amphiphilic polyurethanes have the property, when implanted and seeming not to provoke an inflammatory reaction. Furthermore it is implantation of the polymers, are slowly released at the location of the
A new method to treat blood vessel stenosis using which medicines can be coupled. By coating endovascular improving the bio- and bloodcompatibility of endovascular in human or animal tissue and blood vessels, of remaining possible to incorporate medicines in these polymers which place of implantation. This system can further reduce the	r prosthe prosthe stable h, after	esis with amphiphilic polyurethanes, we have succeeded in significantly ses. These amphiphilic polyurethanes have the property, when implanted and seeming not to provoke an inflammatory reaction. Furthermore it is implantation of the polymers, are slowly released at the location of the
A new method to treat blood vessel stenosis using which medicines can be coupled. By coating endovascular improving the bio- and bloodcompatibility of endovascular in human or animal tissue and blood vessels, of remaining possible to incorporate medicines in these polymers which place of implantation. This system can further reduce the	r prosthe prosthe stable h, after	scular prostheses which are coated with amphiphilic polyurethanes to esis with amphiphilic polyurethanes, we have succeeded in significantly ses. These amphiphilic polyurethanes have the property, when implanted and seeming not to provoke an inflammatory reaction. Furthermore it is implantation of the polymers, are slowly released at the location of the genicity of the prostheses coated with the polyurethanes and inhibit the

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Martritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NB	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE.	Ireland	NZ	New Zealand
BJ	Benin	π	Italy	PL.	Poland
BR	Brazil	л. Л	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Купкуман	RU	Russian Federation
CF CF	Central African Republic	KP	·	SD	
CG	Congo	AF	Democratic People's Republic		Sudan
	_		of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SI	Slovenia
a	Côte d'Ivoire	KZ	Kazakhstan	SK	Slovakia
CM	Cameroon	LI	Liechtenstein	SN	Senegal
CN	China	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LO	Luxembourg	TG	Togo
CZ	Czech Republic	LV	Latvia	LT	Tajikistan
DB	Germany	MC	Monaco	17	Trinidad and Tobaso
DK	Denmark	MD	Republic of Moldova	ŪA	Ukraine
ES	Spain	MG	Madagascar	US	United States of America
FI	Finland	ML	Mali	UZ	Uzhekistan
FR	France	MN	Mongolia	VN	Vict Nam
GA	Gabon			7.14	7 504 6 75000

WO 94/21309

1

POLYURETHANE-COATED INTRAVASCULAR PROTHESES (STENTS) FOR THE TREATMENT OF BLOOD VESSEL STENOSES. A new method to treat blood vessel stenoses by means of endovascular protheses which are coated with amphiphylic polyurethanes to which medicines can be coupled.

10 DESCRIPTION

5

Treatment of blood vessel stenoses by means of a balloon catheter is a popular method. Last year, more than 6,000 patients with coronary heart disease were treated by this method in our country. The problem with this method is on the one hand the danger that a tear occurs during the blowing up of the balloon whereby the blood vessel can close and thus cause an acute myocardial infarction, on the other 20 hand it is well documented that this treatment method is accompanied by a frequent restenosis of the treated blood vessel within 6 months of the treatment. To solve this problems, medicines were tested in order to prevent the restenosis and furthermore new devices were developed. 25 One of these new methods consist of placing a metal intravascular prothesis (stent) at the level of the vessel stenosis. This method is very efficient for treating vesse tears which can occur during balloon dilatation. The problems with this metallic stents however are that they have proven to be thrombogenic and can cause an acute thrombotic occlusion of the treated blood vessel. On the other hand, it appeared that through the inplantation of a metal stent in a blood vessel, the body can react with an inflammatory reaction whereby restenosis within the stent can occur. By covering these endovascular protheses with amphiphylic 35 polyurethanes, we succeeded in significantly limiting both the problem of trombogenecity as well as the problem of reactive hyperproliferative response. Amphiphilic polyurethanes were synthesized starting from 40 amphiphilic polyester diols on the basis of ethylene oxide and proylene oxide. By reaction with a diisocyanate and a chain lengthener (butanediol), a thermoplastic polyurethane is finally obtained. By the appropriate choice of a) the polyesterdiol, especially the proportion of 45 ethyleneoxide/propyleneoxide, and b) the molecular weight of the diol, the bio- and blood compatibility can be optimized. Furthermore the kind of sterilisation of polyurethane-coated devices turned out to be very critical. We used certain amounts of gamma radiation which resulted in the formation of further crossbridging of the polymer leading to a more stable and more elastic polymer which is critical during the stent deployment. The resulting polymers turned out to be very stable when implanted in human or animal tissues or blood vessels. Furthermore they did not provoke 55 any inflammatory reaction.

Furthermore we were able to load these polyurethanes with medicines, which were released slowly at the polymer implantation side. These medicines are used to further decrease the thrombogenecity of the stents (heparin, hirudin, streptokinase, urokinase, tpa and other anticoagulants) and

WO 94/21309 PCT/BE94/00024

2

5

to inhibit the inflammatory reaction caused by the stent (corticosteroids, antimitotics, angiopeptin and other antiinflammatoy drugs.) Using methylprednisolone loaded polyurethane coated stents we were able to block totally the stent restenosis in a pig coronary model.

15

APPLICATION POSSIBILITES OF THE SYSTEM

20

- 1. Treatment of blood vessel stenosis in humans and animals.
- 2. Treatment of complications occurring during other treatment methods of blood vessel stenosis.

25

- 3. Treatment of complications occurring during diagnostic procedures.
- Coating of prosteses, wires, and catheters introduced for
 medical purposes.

WO 94/21309 PCT/BE94/00024

3

5

CLAIMS

10

15

By coating endovascular protheses with amphiphylic polyurethanes, we have developed an efficient method to treat blood vessel stenosis. This method proved to considerably limit the thrombogenicity as well as the rejection against endovascular protheses so that this method signifies an important step forward in the treatment of blood vessel stenosis.

Intern 1al Application No
PCT/BE 94/00024

A. CLASS IPC 5	A61L31/00			
According (to International Patent Classification (IPC) or to both national cla	ssification and IPC		
	S SEARCHED			
Minimum d IPC 5	documentation searched (classification system followed by classific $A61L$	cation symbols)		
Documenta	tion searched other than minimum documentation to the extent th	at such documents are included in the fields \cdot	searched	
Electronic d	data base consulted during the international search (name of data t	nase and, where practical, search terms used)		
C. DOCUM	MENTS CONSIDERED TO BE RELEVANT			
Category *	Citation of document, with indication, where appropriate, of the	relevant passages	Relevant to claim No.	
х	EP,A,O 518 704 (SCIMED LIFE SYST December 1992 see claims 3,4,9-13	TEMS) 16	1	
Y	WO,A,87 04935 (FISCHEL R.E.) 27 1987 see claim 11	August	1	
Y	WO,A,92 15286 (NOVA PHARMACEUTIC September 1992 see page 1, line 9 - line 21; c 1,2,5; example 5		1	
P,A	EP,A,O 566 245 (MEDTRONIC) 20 On see claims 1,3,5,28	ctober 1993	1	
		-/		
X Furt	ther documents are listed in the continuation of box C.	Patent family members are listed	in annex.	
'A' docum	ategories of cited documents : nent defining the general state of the art which is not dered to be of particular relevance	"T" later document published after the int or priority date and not in conflict w cited to understand the principle or t invention	ith the application our	
"E" earlier document but published on or after the international filing date		"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone		
"I," document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or		"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such docu-		
other "P" docum	means ment published prior to the international filing date but than the priority date claimed	ments, such combination being obvious the art. *&* document member of the same paten		
	e actual completion of the international search	Date of mailing of the international s		
] 1	l June 1994	0 8. 06. 9	<u> </u>	
Name and	mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2	Authorized officer		
	N1 2280 11V Ripsynja Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Peltre, C		

2

Inter: 12l Application No
PCT/BE 94/00024

		PCT/BE 9	7/00024
	tuon) DOCUMENTS CONSIDERED TO BE RELEVANT		Determe to plain his
ategory *	Citation of document, with indication, where appropriate, of the relevant passages		Relevant to claim No.
•	US,A,4 371 686 (YAMAMOTO N.) 1 February 1983 see column 1, line 6 - line 22		1
		!	
:			
:			
:			

rnational application No.

PCT/BE 94/00024

Box I	Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)
This inte	ernational search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:
1.	Claims Nos.: because they relate to subject matter not required to be searched by this Authority, namely: "Remark: Although claim 1 is directed to a method of treatment of the human/animal body the search has been carried ot and based on the alleged effects of the product."
2.	Claims Nos.: because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3.	Claims Nos.: because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).
Box II	Observations where unity of invention is lacking (Continuation of item 2 of first sheet)
This Inte	ernational Searching Authority found multiple inventions in this international application, as follows:
ı. 🗌	As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2.	As all searchable claims could be searches without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
з. 🗌	As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4.	No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:
Remark	on Protest The additional search fees were accompanied by the applicant's protest. No protest accompanied the payment of additional search fees.

...formation on patent family members

Inter nal Application No
PCT/BE 94/00024

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP-A-0518704	16-12-92	JP-A-	5200048	10-08-93
WO-A-8704935	27-08-87	DE-A- EP-A,B EP-A- US-A-	3786721 0257091 0556940 4768507	02-09-93 02-03-88 25-08-93 06-09-88
WO-A-9215286	17-09-92	AU-A-	1579092	06-10-92
EP-A-0566245	20-10-93	JP-A-	6007455	18-01-94
US-A-4371686	01-02-83		1184116 57051718 58008700	27-12-83 26-03-82 17 - 02-83